

CERAMIC NOTES

SKETCH

FINAL RESULT

ADDITIONAL NOTES

DESIGN NAME, DATE

CLAY

THROWN

H: DATE FIRED:

W: CONE:

D: HOLD / SOAK:

WEIGHT: TEMPERATURE:

GLAZE APPLICATION

DETAILS

GLAZED

H: DATE FIRED:

W: CONE:

D: HOLD / SOAK:

WEIGHT: TEMPERATURE:

SHRINKAGE:

RATING

CERAMIC NOTES

Tumbler 2/2/26

DESIGN NAME, DATE

CLAY

S10 Toffee

> Light beige / warm off-white

THROWN

H: 11.5 cm

DATE FIRED: 2/12/26

W: 9.5 cm

CONE: 6

D: 9.0 cm

HOLD / SOAK: 10 min

WEIGHT: 520 g

TEMPERATURE: 950 °C

GLAZE APPLICATION

① Opal White / 1 coat (dip)

② Ice Crystal / 2 coats (dip)

③ Plus / 1 coat (brush)

○

○

○

DETAILS

Applied Plus with a soft brush with
one controlled coat

Minimal overlap

GLAZED

H: 10.8 cm

DATE FIRED: 2/20/26

W: 8.9 cm

CONE: 6

D: 8.5 cm


HOLD / SOAK: 30 min

WEIGHT: 500 g

TEMPERATURE: 1230 °C

SHRINKAGE: 6%

RATING



SKETCH



FINAL RESULT

ADDITIONAL NOTES

Great glaze result Strong flow

Use less Plus next time

Test slow cool